



# PRODUCT INFORMATION



<b>Product Name:</b>	<b>DACPOL 9</b>
<b>Reference Number:</b>	9-Line
<b>Coating Type:</b>	Urethane alkyd
<b>Typical Uses:</b>	Single-pack polyurethane enamel giving tough, durable, abrasion-resistant coating. Resists mild chemicals, oils, grease, etc. Interior use only.
<b>Colours Available:</b>	Full range to special order – subject to a 75 litre minimum order quantity.
<b>Appearance of Dried Film:</b>	Gloss
<b>Volume Solids:</b>	50 % - may vary with colour.
<b>Dry Film Thickness:</b>	<b>Typical:</b> 40 microns <b>Range:</b> 30-50 microns
<b>Theoretical Coverage:</b>	12.5m <sup>2</sup> per litre at 40 microns dry film thickness.
<b>Drying Time at 20°C:</b> (Will vary with temperature, air movement etc.)	<b>Touch Dry:</b> 1.5 hours <b>Firm Dry:</b> 4 hours <b>Overcoat:</b> overnight
<b>Packaging:</b>	5 litre lever lid tins
<b>Shelf Life:</b>	2 years in unopened containers, when stored under cover in good storage conditions.
<b>Storage:</b>	Under cover within temperature range of 5°C to 32°C.

**Continued/**

**Ref: 9-line**

- Surface Preparation:** Normally applied over suitably primed and/or undercoated surfaces (i.e. Dacrylate 95-line, 98-line primers, Alkysil Undercoat, etc.).
- Application:** May be applied by brush or conventional spray.
- Airless spray quality available to special order.
- Conventional Spray
- May require addition of 10-15% Dacrylate Thinner R70 to achieve optimum spray characteristics.
- Apply to an approximate wet film thickness of 90 microns to achieve a dry film thickness of 40 microns.
- Clean Up:** Dacrylate Thinner R1 or R70
- Health and Safety:** Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

**Issued:** November 2001 SW/DAE/WHC