



PRODUCT INFORMATION



Product Name:	DACRYLUX
Reference Number:	101-Line.
Coating Type:	Acrylic latex.
Typical Uses:	Versatile water-borne low-odour coating for internal and external use, for suitable primed wood, masonry and steel. Microporous, good flexibility, non-flammable and non-toxic.
Colours Available:	White (full range to special order).
Appearance of Dried Film:	High sheen.
Volume Solids:	30% (may vary with colour).
Dry Film Thickness:	Typical: 40 microns.
Theoretical Coverage:	7.5m ² per litre at 40 microns dry film thickness.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 1 hour. Firm Dry: 3 hours. Overcoat: 3 hours.
	NB: Drying times will vary depending on humidity, air circulation, ventilation etc.
Packaging:	5 litre containers.
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C. Protect from frost.

Continued/

Surface Preparation:

Masonry, Concrete, Brickwork, Plaster etc

- i) Ensure substrate is fully cured, clean and dry.
- ii) Apply one coat of Clear Masonry Sealer, ref:150-50.
- iii) Apply one coat of A.C. Universal Primer, ref:115-line.
- iv) Apply two coats of Dacrylux.

Woodwork

- i) Ensure substrate is clean and dry.
- ii) Apply one coat of A.C.Universal Primer, ref:115-line.
- iii) Apply two coats of Dacrylux.

Old Paintwork

- i) Ensure substrate is clean, dry with good adhesion.
- ii) Apply one/two coats of Dacrylux.

Steelwork

- i) Prepare and degrease metal substrate and apply one coat of Dacquacote Primer, ref:120-line.
- ii) Apply two coats of Dacrylux.

Galvanised Steel

- i) Degrease galvanised surface and treat with Dacrylate Mordant Solution, ref:150-23.
- ii) Apply one coat of Dacquacote Primer, ref:120-line.
- iii) Apply one/two coats of Dacrylux.

Note: Do not apply in wet conditions or high humidity. Protect from rain for at least 4 hours. Do not apply at ambient temperatures below 4°C.

Clean Up:

Clean all equipment **IMMEDIATELY** after use with clean water.

Health and Safety:

Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.