



PRODUCT INFORMATION



Product Name:	DUAL PRIMER
Reference Number:	52-Line
Coating Type:	Alkyd-based.
Typical Uses:	Wood colouring and priming basecoat for interior and exterior use. May be overcoated with conventional paint or wood stain. Microporous to control water-vapour diffusion. Pigmentation minimises degradation of timber by ultra-violet sunlight.
Colours Available:	Yellow Ochre – Ref:52-11. (Other colours to special order, may be subject to minimum order requirement.)
Appearance of Dried Film:	Low sheen.
Application Rate:	Approximately 15m ² per litre depending upon the porosity of timber, film build etc.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 1 hour. { Firm Dry: 3 hours { When applied to softwood. Overcoat: Overnight. {
Packaging:	5 litre and 20 litre containers.
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.
Surface Preparation:	All timber should be adequately preserved, clean, dry and free of contaminants. Lightly sand in direction of grain to give smooth finish.
Application:	Apply by brush, dipping, spray or automatic timber coater.
Clean Up:	Dacrylate Thinner R1.
Health and Safety:	Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.