



# PRODUCT INFORMATION



<b>Product Name:</b>	<b>DACRYLATE ACRYLIC SEALER FOR MASONRY</b>
<b>Reference Number:</b>	59-10
<b>Coating Type:</b>	Solvent-based acrylic.
<b>Typical Uses:</b>	Penetrating sealer for <b>uncoated</b> masonry substrates, prior to application of the Dacrylate Acrylic System for Masonry.
<b>Colours Available:</b>	“Clear” with ‘tracer’ of white pigment.
<b>Theoretical Coverage:</b>	Varies considerably depending on porosity of substrate, but typically in the range of 4-10m <sup>2</sup> per litre.
<b>Drying Time at 20°C:</b> (Will vary with temperature, air movement etc.)	<b>Touch Dry:</b> 20 minutes. <b>Firm Dry:</b> 2 hours. <b>Overcoat:</b> 2 hours.
<b>Packaging:</b>	5 litre containers.
<b>Shelf Life:</b>	12 months in unopened containers, when stored under cover in good storage conditions.
<b>Storage:</b>	Under cover within temperature range of 5°C to 32°C.
<b>Surface Preparation:</b>	<b>1) New Rendering</b> Ensure completely cured and dry, remove all dust, friable material, etc., to give a clean, dry sound substrate. <b>2) Old Rendering Where Previous Paint Burnt Off</b> Thoroughly scrape and wire brush to remove all burnt paint, carbon deposits, etc., to leave clean, sound substrate.
<b>Application:</b>	Stir well before use. Apply by brush, ensuring complete coverage and penetration into crevices, rough profiles, etc.
<b>Clean Up:</b>	Dacrylate Thinner R8
<b>Health and Safety:</b>	Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

**Issued:** October 2001 SW/DAE/CR/WHC