



PRODUCT INFORMATION



Product Name:	<u>DACRYLATE ACRYLIC MASONRY FINISH</u>
Reference Number:	59-Line
Coating Type:	Solvent-based acrylic with microporous properties.
Typical Uses:	Highly durable masonry finish with outstanding flexibility, colour retention, and low dirt retention. Microporous allowing permeation of water vapour.
Colours Available:	White - Ref:59-8 (Full range available to special order. May be subject to minimum order requirements.)
Appearance Of Dried Film:	Gloss.
Volume Solids:	40%.
Dry Film Thickness:	Typical: 40 microns.
Theoretical Coverage:	10m ² per litre at 40 microns.
Drying Time At 20°C: (Will Vary With Temperature, Air Movement, etc.).	Touch Dry: 1 hour. Firm Dry: 2 hours. Overcoat: 2 hours.
Packaging:	5 litre containers.
Shelf Life:	12 months in unopened containers when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.

Continued/

Ref: 59-Line

Surface Preparation:

In order to gain the advantages of the microporous system, the Dacrylate Acrylic Masonry System coatings must be applied to a clean, sound uncoated substrate. Old coatings should be removed by abrasive blasting or burning-off.

Dacrylate Acrylic Masonry System, however, may be applied over aged paint systems provided they are clean and sound with good adhesion.

New or unpainted substrates should be sealed with Dacrylate Acrylic Sealer, ref:59-10.

Previously painted and sealed surfaces should be coated with one coat of Dacrylate Acrylic Masonry Undercoat followed by two coats of Dacrylate Acrylic Masonry Finish.

Application:

Apply by brush to a wet film thickness of approximately 100 microns to achieve a dry film thickness of 40 microns.

Note: A specification sheet is available giving full details of surface preparation, application, etc.

Clean-Up:

Dacrylate Thinner R8.

Health And Safety:

Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage, etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.